



International werkstoff sammenligning

W.-Nr.	DIN	AISI ¹⁾	SS ²⁾	AFNOR ³⁾	BS ⁴⁾
1.4005	X 12 CrS 13	416	2380	Z 11 CF 13	416 S 21
1.4006	X 10 Cr 13	410	2302	Z 10 C 13	410 S 21
1.4016	X 6 Cr 17	430	2320	Z 8 C 17	430 S 15
1.4021	X 20 Cr 13	420	2303	Z 20 C 13	420 S 37
1.4028	X 30 Cr 13	420	2304	Z 30 C 13	420 S 45
1.4034	X 46 Cr 13		(2304)	Z 40 C 14	(420 S 45)
1.4057	X 20 CrNi 17 2	431	2321	Z 15 CN 16,02	431 S 29
1.4104	X 12 Cr MoS 17	430 F	2383	Z 13 CF 17	(441 S 29)
1.4105	X 4 Cr MoS 18	430 F		Z 8 CF 17	
1.4112	X 90 CrMoV 18	440 B			
1.4113	X 6 CrMo 17 1	434			434 S 17
1.4122	X 35 CrMo 17				
1.4125	X 105 CrMo 17	440 C		Z 100 CD 17	
1.4301	X 5 CrNi 18 10	304	2332	Z 6 CN 18.09	304 S 15
1.4303	X 5 CrNi 18 12	305/308		Z 5 CN 18.11 FF	305 S 17
1.4305	X 10 CrNiS 18 9	303	2346	Z 8 CNF 18.09	303 S 31
1.4306	X 2 CrNi 19 11	304 L	2352	Z 2 CN 18.10	304 S 11
1.4310	X 12 CrNi 17 7	301	2331	Z 12 CN 18.08	310 S 22
1.4313	X 5 CrNi 13 4	E 415	2384	Z 4 CND 13.4	425 C 11
1.4401	X 5 CrNiMo 17 12 2	316	2347	Z 7 CND 17.12.02	316 S 31
1.4404	X 2 CrNiMo 17 13 2	316 L	2348	Z 3 CND 18.12.02	316 S 11
1.4435	X 2 CrNiMo 18 14 3	316 L	2353	Z 3 CND 18.14.03	316 S 11
1.4436	X 5 CrNiMo 17 13 3	316	2343	Z 7 CND 18.12.03	316 S 11
1.4460	X 4 CrNiMoN 27 5 3	329	2324	Z 5 CND 27.05 AZ	
1.4462	X 2 CrNiMoN 22 5 3	329 A/F 51	2377	Z 3 CND 22.05	
1.4539	X 1 NiCrMoCuN 25 20 5		2562	Z 1 NCDU 25.20	
1.4541	X 6 CrNiTi 18 1 0	321	2337	Z 6 CNT 18.10	321 S 31
1.4511	X 6 CrNiNb 18 10	347	2338	Z 6 CNNb 18.10	347 S 31
1.4567	X 3 CrNiCu 18 9	304 K		Z 6 CNU 18.10	
1.4571	X 6 CrNiMoTi 17 12 2	316 Ti	2350	Z 6 CNDT 17.12	320 S 31
1.4580	X 6 CrNiMoNb 17 12 2	316 CB		Z 6 ZNDNB 17.12	
1.4713	X 10 CrAj 7			Z 8 CA 7	
1.4742	X 10 CrAj 18			Z 10 CAS 18	
1.4762	X 10 CrAj 24	(446)	(2322)	Z 10 CAS 24	
1.4828	X 15 CrNiSi 20 12	309		Z 15 CNS 20.12	309 S 24
1.4841	X 15 CrNiSi 25 20	314		Z 12 CNS 25.20	314 S 25

¹⁾ AISI: American Iron and steel Institute ²⁾ SS: Swedish Standard ³⁾ AFNOR: Association Francaise de Normalisation ⁴⁾ BS: British Standard